

ADHESIVE TYPE	RH LEVEL	ADHESIVE
<p>ROLL-ON/ TROWEL</p>	<p>NO limit for new construction & above-grade renovations</p> <p>95% for on-grade renovations</p>	<p>Non-Reactive Standard</p> <ul style="list-style-type: none"> NEW CONSTRUCTION: Approved for all new construction installations with NO pH or RH limits <p>INSTALL 60 days after new pour with RH testing</p> <ul style="list-style-type: none"> RENOVATION: Above-grade renovations: NO pH or RH limits / On-grade renovations (without vapor retarder): RH of 95%, NO pH limit
<p>SPRAY</p>	<p>over 98%</p>	<p>Mosaic Moisture XT-Spray</p> <ul style="list-style-type: none"> NEW CONSTRUCTION: Approved for all new construction installations with NO pH or RH limits and NO vapor retarder required. <p>INSTALL 30 days after new pour / NO testing required</p> <ul style="list-style-type: none"> RENOVATION: Approved for all renovation installations with NO pH or RH limits
<p>ADHESIVE-FREE</p> <p>Milliken TractionBack®</p>	<p>NO limit for new construction</p> <p>85% for on-grade renovations</p>	<p>TractionBack®</p> <ul style="list-style-type: none"> NEW CONSTRUCTION: Approved for all new construction installations with no pH or RH limits NO pH or RH testing required <p>INSTALL 90 days after new pour</p> <ul style="list-style-type: none"> RENOVATION: Above-grade renovations: NO pH or RH limits / On-grade renovations: RH of 85%, NO pH limit
	<p>NO limit</p>	<p>TractionBack® Plus</p> <ul style="list-style-type: none"> NEW CONSTRUCTION/RENOVATION: Approved for all installations with NO pH or RH limits <p>INSTALL 30 days after new pour (new construction)</p>