






Adhesives

LVT



ADHESIVE TYPE	RH LEVEL	ADHESIVE	LVT TYPE
TROWEL 	up to 95%	LVT Standard <ul style="list-style-type: none"> For on-grade installations vapor retarder required Approved for all grade renovations where concrete pH levels are between 5-12 and RH is less than 95% <div style="border: 1px solid black; padding: 2px; display: inline-block;">INSTALL</div> 45 days after new pour with RH testing	2 mm, 2.5 mm & 5 mm FlexForm™ LVT
	over 95%	LVT Moisture XT with Acousti-Loc Technology <ul style="list-style-type: none"> For use where very high moisture is a concern NO vapor retarder required NO moisture testing is required NO RH or pH limits <div style="border: 1px solid black; padding: 2px; display: inline-block;">INSTALL</div> 45 days after new pour / NO testing required	2 mm, 2.5 mm, 5 mm FlexForm™ LVT
SPRAY 	up to 98%	Mosaic 98 - Spray <ul style="list-style-type: none"> Approved for all grade renovations where concrete pH levels are between 5-11 and RH is equal to or less than 98%. <div style="border: 1px solid black; padding: 2px; display: inline-block;">INSTALL</div> 45 days after new pour with RH testing	2 mm, 2.5 mm, 5 mm FlexForm™ LVT 5 mm FlexForm Sound™ LVT* <small>*Hospitality Rooms only, no public areas</small>
	over 98%	Mosaic Moisture XT-Spray <ul style="list-style-type: none"> For use where very high moisture is a concern. NO moisture testing is required. NO RH or pH limits. <div style="border: 1px solid black; padding: 2px; display: inline-block;">INSTALL</div> 45 days after new pour / NO testing required	5 mm FlexForm™ LVT
TROWEL 	up to 95%	Mosaic 95 <ul style="list-style-type: none"> Approved for all grade renovations where concrete pH levels are between 5-11 and RH is equal to or less than 95% <div style="border: 1px solid black; padding: 2px; display: inline-block;">INSTALL</div> 45 days after new pour with RH testing	5 mm FlexForm™ LVT 5 mm FlexForm Sound™ LVT